

**ADVANTAGE REFINISH PRODUCTS**  
**TECHNICAL DATA INFORMATION**  
**DATED: OCTOBER 2022**

**DESCRIPTION**

ADVANTAGE #350 (GRAY) is a hypercure, high solids, high build 2K Acrylic Urethane Primer Filler/Surfacer/Sealer. This unique product provides optimal color holdout and can be sanded within 45-60 minutes, with minimal sand scratch swelling. Mixed with the optional DTS-Direct to Substrate Hardener, ADV350 is designed to be used on properly prepared steel, galvanized, aluminum, fiberglass and previously painted surfaces. NOTE: Plastic surfaces should be treated with 5 STAR ADVANTAGE #59007 Adhesion Promoter. ADV350 is inherently 2.1 VOC without expensive solvents, and dries to a smooth low sheen finish, with built-in guide coat properties.

**PRODUCTS**

#350-01	DTS Hypercure 2K Primer Gray 2.1 VOC	Gallon
#351-04	Standard Activator (non-DTS) 2.1 VOC	Quart
#352-04	DTS Activator 2.1 VOC	Quart
#353-04	DTS Sealer Activator 2.1 VOC	Quart

*Three products in one!*

**MIXING RATIO**

**Primer – Filler (4:1)**

Mix 4 parts #350 Primer to 1 part #351/352 Primer Activator (activator choice depends upon application)

**Primer – Surfacer (4:1:1)**

Mix 4 parts #350 Primer to 1 part #351/352 Primer Activator and up to 1 part Urethane Reducer (0 VOC Urethane Reducer in compliant areas) (activator choice depends upon application)

**Primer – Sealer (4:1:2)**

Mix 4 parts #350 Primer to 1 part #353 Primer Sealer Activator and up to 2 parts Urethane Reducer (0 VOC Urethane Reducer in compliant areas)

**POT LIFE** Pot life will be approx.1 hour.

**SURFACE PREPARATION**

Use Wax & Grease Remover to clean substrate free of grease, dirt and foreign contaminants.

**APPLICATION DIRECTIONS**

Apply 2-3 medium wet coats to desired film thickness  
Allow 10-15 minutes between coats.  
Clean gun after spraying is completed.

**DRY / FLASH TIMES**

Air Dry @ 77°F	
Flash between coats	10-15 minutes
Sand and Top Coat	45-60 minutes

**GUN SET UPS**

Conventional	
Gravity Feed	1.4mm – 1.8mm
Siphon Feed	1.4mm – 1.8mm

**AIR PRESSURES**

Conventional at the Gun	
Gravity Feed	30-40 psi
Siphon Feed	35-45 psi
HVLP at the cap	8-10 psi

**CLEAN UP**

Use Urethane Reducer, Lacquer Thinner or Zero VOC Solvents. Check your local regulations.

**PHYSICAL DATA**

Solids wt. NR reducers VOC (as mixed):  
Primer Filler 71% / Primer Surfacer 63% / Sealer 53%

Solids wt. 2.1 VOC with 0 VOC reducers (as mixed):  
Primer Filler 71% / Primer Surfacer 64% / Sealer 57%

Solids Vol NR and 2.1 VOC (as mixed):  
Primer filler 52%

Color: Light Gray

**NOTE: ADVANTAGE products are not recommended for use in temperatures below 60° F. Use below these temperatures will affect dry times and performance.**

**FOR INDUSTRY USE ONLY****Read SDS Before Use**

The contents of the package must be blended with other components before the product can be used. Any mixture of components will have hazards of all components. Before opening the packages, read all warning labels. Follow all precautions. The material is designed for application only by professionally trained personnel using proper equipment under controlled conditions, and is not intended for sale to the general public.

**SEE SDS AND PRODUCT LABELS FOR ADDITIONAL SAFETY INFORMATION.**

**[WWW.ADVANTAGEREFINISH.COM](http://WWW.ADVANTAGEREFINISH.COM)**